



Mito





Mito

This luxurious flatwoven quality belongs to our Comfort Collection. A collection that consists only of soft, voluminous and elegant upholstery textiles.

Mito has been woven on an air jet loom, it is piece dyed and has been laminated with a thick non-woven backing. Our product development team wanted to develop a rough structure, which is durable, strong and suitable for all types of upholstery, we found an answer on these points with Mito. We hope that you are just as excited as we are about these 22 deep, soft and modern colours, which are available from stock.

Last but not least, it is machine-washable at 30 degrees Celsius* and also easy to clean due to the damp and dirt prevented finish.

- We recommend to wash the cover inside out and immediately place the cover back to the piece of furniture, slightly damp, after washing.
- Please note that during washing the damp- and dirt prevented treatment will disappear faster.
- Dirt and damp prevention treatment applied.


***Textafoam originals** Established in 1970, this Dutch family business brings together craftsmen in textiles and furniture design to build an unrivalled portfolio in upholstery fabrics that meets buyer's needs every time. Featuring a wide colour range, ultimate value for money and excellent reliability in the supply chain.*

Composition


/ faceside 90%PES 10%NY
/ backside 100%PES
/ chenille flatweave

Suitable for


sofa's, beds, chairs with fitted and loose fitting upholstery




anthracite 67




ashgrey 40




azure 144



beige 05




blue 45



blush 92 (new colour)



brass 170 (new colour)



burgundy 34




cinnamon 94



cognac 28




desert 109




darkgrey 68


Please note: colours may vary according to your screen settings.




dolphin 180




green 55




hunter 156




iceblue 43



lightgrey 60 (new colour)




liver 10




mushroom 215 (new colour)




mustard 06




natural 01



onyx 169




pale 200




pearl 106


Please note: colours may vary according to your screen settings.



sage 203 (new colour)



slate 87



steel 149

Please note: colours may vary according to your screen settings.

Mito - Article passport

A piece dyed, durable and strong article with a rough structure.

Available from stock in a wide range of contemporary and commercial colours.

Product characteristics

Productgroup	chenille flatweave
Applications	sofa's, beds, chairs with fitted and loose fitting upholstery
Composition faceside	90%PES 10%NY
Composition backside	100%PES
Bonding	non-woven
Statistic code	54075200
Dyeing method	piece dyed
Available colours	27
Packaging	transparent plastic

Durability specifications

Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Dry	Wet	DGM	DGM+	
Abrasion resistance - yarn breakage	DIN EN ISO 12947-1:2007-04, DIN EN ISO 12947-2:2017-03	CTL	cycles	40.000		min. 8.000	min. 16.000	B
Pilling	DIN EN ISO 12945-2:2000-11. 2000 cycles	CTL	grade	4		min. 3-4	min. 4	B
Colour fastness to light	DIN EN ISO 105-BO2:2014-11. Process 3, exposure level 5							
	light colours	CTL	grade	4		min. 4	min.5	C
	middle colours	CTL	grade	5		min. 4	min.5	B
Colour fastness to rubbing	DIN EN ISO 105-X12:2016-11							
	light colours	CTL	grade	5	5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
	middle colours	CTL	grade	5	4-5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A
dark colours	CTL	grade	4-5	4-5	dry: 4, wet: 3	dry: > 4, wet: 3-4	A/A	
	Ignitability (cigarette test)	BS 5852 part 1 (1979) from The Furniture and Furnishing (Fire) (Safety) regulations: 1988 No. 1324. Schedule 4 part 1 Ignition source 0: cigarette	CTL	passed				

Processing specifications

Minimum workable width in centimeters	± 143							
Roll length in meters	± 40							
Material weight in grams per linear meter	± 493							
Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Tensile strength	DIN EN ISO 13934-1:2013-08	CTL	Newton	1.046	496	min. 350	min. 400	A/B
Tear growth resistance	DIN EN ISO 13937-3:2000-06	CTL	Newton	70,3	96,6	min. 25	min. 30	A/A
Resistance to seam slippage	DIN EN ISO 13936-2:2004-07. Load 180 N	CTL	mm	2,7	2,9	max. 5	max. 4	A/A
Delamination	DIN 53530:1981-02	CTL	Newton	40,0	31,7	n/a	n/a	n/a
Chemical substances	REACH	Centexbel	passed					
	Oeko-Tex, product class II	Centexbel	certified					

Cleaning specifications

Test	Test specification	Executed by laboratory:	Unit	Testresult		Norm RAL GZ 430/4:2019-01		Norm DIN EN 14 465:2006-09
				Warp	Weft	DGM	DGM+	
Dimensional change for washing 30 degrees celcius / air drying	DIN EN ISO 5077:2008-04, DIN EN ISO 6330:2013-02, DIN EN ISO 3759:2011-08	CTL	%	0,0	-1,2	n/a	n/a	A/A



- We recommend to wash the cover inside out and immediately place the cover back to the piece of furniture, slightly damp, after washing.
 - Please note that during washing the damp- and dirt prevented treatment will disappear faster.
 - Dirt and damp prevention treatment applied.



Textaafoam
creativity in fabrics

Textaafoam b.v.
La Défense 11 | 5026 SC Tilburg
P.O. Box 12 | 5050 AA Goirle
The Netherlands

T +31(0)13 534 5934
F +31(0)13 534 7586
E info@textaafoam.nl
www.textaafoam.nl